







Carecoat Barrier is a wear resistant water based liquid product especially formulated to leave a thin, temporary film on cargo hold surfaces. The film provides a barrier between the cargo and the cargo hold surfaces making the cleaning operation after unloading quicker and easier with an excellent cleaning result.

#### **ADVANTAGE**

- New generation water based coating
- Wear resistant
- High environmental sustainability
- Reduced cleaning time
- Easy to apply and easy to remove
- Non staining does not contain any silicones, solvents or phosphates
- Safe to use on all surfaces
- Will not contaminate exposed cargo

#### **APPLICATION**

Carecoat Barrier is applied to cargo holds to prevent cargoes like cement powder, coal/pet coke, fertilizers, grains, salt/sulfur or iron ores to stick and/ or stain the cargo holds. Resulting in savings: reduced cleaning time, shorter turn around times and reduced cleaning product consumption.

#### **DIRECTIONS FOR USE**

Before applying Carecoat Barrier make sure the surface is thoroughly cleaned. When the surface is dry Carecoat Barrier is applied directly from the drum as a ready to use mixture. Spray the liquid on the cargo hold surfaces by use of suitable low-pressure spraying equipment like our Caretech Foam Cleaning Kit.



- Eco-friendly
- Biodegradable
- Excellent protection
- Wear resistant
- Reduced
  cleaning time
- Easy to apply

MARINE CARE BV Mozartlaan 3 3144 NA Maassluis The Netherlands T. +31 (0)10 2950342 F. +31 (0)10 2950345 E. supply@marinecare.nl

# DIRECTIONS FOR USE (CONTINUED)

As soon as the surface appears wet, a proper film is created. There is no need to apply more than necessary. Allow the film to dry completely before loading the cargo. Depending on the air temperature and humidity this will take between 1 - 2 hours.

To remove Carecoat Barrier from the cargo holds use a 10 % solution of IMO approved Careclean Alkaline or Alkaline Extra. Spray the solution on the surface and let soak for 20 - 30 minutes, then rinse off with plenty of water.

# COVERAGE/ FILM THICKNESS

1 liter of Carecoat Barrier will cover 15 - 20 per m<sup>2</sup>. The coating is supplied ready for use – do not dilute.

# **PROPERTIES**

Article number pH Density Flashpoint Physical state 14303 / 16303 9 1,01 g/cm<sup>3</sup> > 100 °C Liquid

### **APPROVALS**

All our supplied chemicals are IMO approved & comply with the Marpol MEPC 63/23/add. 1, Annex 24 resolution MEPC.219(63) – Annex V – 2012 guidelines adopted March 2012.

For detailed information on safety and health, please refer to the Material Safety Data Sheet MSDS and/or product label.



CARECOAT BARRIER

- Eco-friendly
- Biodegradable
- Excellent protection
- Wear resistant
- Reduced
  cleaning time
- Easy to apply

liscover the difference

#### MARINE CARE BV Mozartlaan 3 3144 NA Maassluis The Netherlands T. +31 (0)10 2950342 F. +31 (0)10 2950345 E. supply@marinecare.nl W. www.marinecare.nl

This information is based on data that we believe to be accurate and reliable and is intended to be used by persons having the knowledge and skill to apply this product properly. We assume no responsibility for results or damages incurred from their use by the Buyer. No liability (including liability for negligence) will attach to Marine Care or its servants or agents arising out of or in connection with or in relation to this product information.