



CARECLEAN F DESCALEX P

Inhibited acid cleaning powder for removal of water scale and rust deposits from water systems

DESCRIPTION

Careclean F Descalex P is an inhibited sulphamic acid based descaler and rust remover. Careclean F Descalex P is used for acid cleaning of boilers, condensers, diesel coolingwater systems, evaporators, butterworth heaters, pipe systems etc.

ADVANTAGE

- Inhibited to prevent acidic attack on surfaces to be cleaned
- Safe on rubber, plastic and jointing materials
- Easy to handle
- Suitable for most common ferro and non-ferro metals

APPLICATION

- Descaling of diesel cooling water systems
- Cleaning and scale removal from air coolers sea water side.
- Scale and rust scale removal from boilers, condensers, evaporators, heat exchangers, etc.

DIRECTIONS FOR USE

- We recommend that a preliminary test is carried out on samples of the original scale deposits in order to select the most suitable acid cleaner and optimize concentration and temperature conditions.
- When a boiler is soiled with light oil deposits or if silicates and/or calcium sulphates are present, boiling out with Careclean Alkaline Extra is recommended.
- If heavy mineral oil deposits are present in a boiler or cooling system, a preliminary treatment with an emulsifying cleaner, like Careclean Degreaser GP is recommended.

- Eco-friendly
- Biodegradable
- Excellent scale removal
- Easy handling and storage
- Suitable on most metals
- Approved by:
 - > Marinfloc

discover the difference

MARINE CARE BV
Mozartlaan 3
3144 NA Maassluis
The Netherlands
T. +31 (0)10 2950342
F. +31 (0)10 2950345
E. supply@marinecare.nl
W. www.marinecare.nl



Circulation Method:

Before cleaning with a Careclean F Descalex P solution, we recommend to thoroughly rinse with water; this will partly or completely remove loose sludge, scale, etc.

Depending on the nature of the scale and degree of contamination, it is recommend to use a cleaning solution with a concentration of 3 - 10 kgs Careclean F Descalex P per 100 liters of water. This solution has to be prepared by continuously stirring the powder into warm water.

Solutions of Careclean F Descalex P may be heated to a maximum of 60 °C, which will result in a quicker cleaning process.

During the cleaning process, inflammable and/or toxic gases are possibly formed, therefore adequate ventilation must be provided. Avoid open fire. The length of the cleaning operation depends on the thickness and type of deposit and also on the product concentration. Generally speaking this period will be within 24 hours.

After cleaning, drain off the solution and neutralize it with Careclean Alkaline Extra outside the system.

The final rinsing should be carried out with a 1% solution of Careclean Alkaline Extra.

Cleaning in immersion baths:

Fill a plastic or plastic-lined bath with a solution of Careclean F Descalex P in water. (1 kg Careclean F Descalex P to 10 liters water).

Solutions of Careclean F Descalex P can be heated to a maximum of 60° C for a quicker cleaning process. Introduce the components to be cleaned into the bath and let them soak for a maximum of 24 hours, depending on the degree of scaling. Remove the components from the bath and rinse them with a powerful waterjet.

CAUTION:

Suitable for most common ferro and non-ferro metals, except zinc, aluminium and galvanised materials.

DOSAGE

Circulation	3 - 10 %	solution
Immersion bath	10 %	solution

PROPERTIES

Article number	14201
pH (1% solution in water)	1,5
Density	1,2 g/cm ³
Flashpoint	Not applicable
Physical state	Powder

APPROVALS

- Marinfloc Approved OWS Compatible

For detailed information on safety and health, please refer to the Material Safety Data Sheet MSDS and/or product label.

CARECLEAN F DESCALEX P

- Eco-friendly
- Biodegradable
- Excellent scale removal
- Easy handling and storage
- Suitable on most metals
- Approved by:
> Marinfloc

discover the difference

MARINE CARE BV
Mozartlaan 3
3144 NA Maassluis
The Netherlands
T. +31 (0)10 2950342
F. +31 (0)10 2950345
E. supply@marinecare.nl
W. www.marinecare.nl